

FUMERIC RESIN KPM– 950



TYPE: GHYCEROL MODIFIED RESIN.

PROPERTIES: Medium viscosity in solvents and quick release.

CONSTANTS: Melting Point 125°C - 130°C.
Acid Value 110 – 120.

SOLUBILITY: Soluble in aromatic solvent and in alcohol insoluble in aliphatic hydrocarbons.

COMPATIBILITY: Compatible with N.C. and Polyamide Resin. Mainly used for the modification of Polyamide based inks, and water based ink.